



商品名

A5052P-0

JIS規格アルミニウム及びアルミニウム合金板

JIS-H 4000

板厚 (mm)	1000×2000 (mm)	1250×2500 (mm)	1525×3050 (mm)	2000×4000 (mm)	引張強さ N/mm ²	耐力 N/mm ²	伸び %
0.8	◎				170以上 215以下	65以上	17以上
1.0	◎						
1.5	◎						
1.6	◎	◎					19以上
2.0	◎	◎					
2.5	◎						
3.0	◎	◎	◎				
4.0	◎						
5.0	◎						
6.0		◎		◎			18以上
8.0			◎	◎			
10.0			◎	◎			
12.0		◎	◎	◎			
15.0		◎		◎			
20.0		◎	◎				
22.0		◎	◎				
35.0			◎				
70.0			◎				

A5083P-O

JIS規格アルミニウム及びアルミニウム合金板

JIS-H 4000

板厚 (mm)	1000×2000 (mm)	1250×2500 (mm)	1525×3050 (mm)	2000×4000 (mm)	引張強さ N/mm ²	耐力 N/mm ²	伸び %
55.0		◎	◎		270以上 345以下	115以上 200以下	16以上
60.0		◎	◎				
65.0	◎	◎	◎				
70.0		◎	◎				
80.0		◎	◎				
85.0		◎			260以上	110以上	
90.0		◎	◎				
100.0		◎	◎				
105.0			◎				
110.0		◎	◎		(260以上)	(110以上)	(16以上)
120.0		◎	◎				
130.0		◎	◎				
140.0			◎				
150.0			◎				
160.0		◎					
190.0		◎					

()の数字は機械的性質の規格値がないため、メーカー標準値