



商品名

A5052P-H112

JIS規格アルミニウム及びアルミニウム合金板

JIS-H 4000

板厚 (mm)	1000×2000 (mm)	1250×2500 (mm)	1525×3050 (mm)	引張強さ N/mm ²	耐力 N/mm ²	伸び %
8.0	◎	◎	◎	195以上	110以上	7以上
10.0	◎	◎	◎			
12.0	◎	◎	◎			
15.0	◎	◎	◎	175以上	65以上	12以上
16.0	◎	◎	◎			
18.0	◎	◎	◎			
20.0	◎	◎	◎			
25.0	◎	◎	◎			
30.0	◎	◎	◎			
35.0		◎	◎			
40.0		◎	◎			
45.0		◎	◎			
50.0		◎	◎			
55.0		◎	◎			
60.0		◎	◎	(175以上)	(65以上)	16以上
65.0		◎	◎			
70.0		◎	◎			
80.0		◎	◎			
90.0		◎	◎			
100.0		◎	◎			
110.0			◎			
120.0		◎	◎			
130.0		◎	◎			
140.0		◎	◎			
150.0	◎	◎	◎			(16以上)

()の数字は機械的性質の規格値がないため、メーカー標準値