



商品名

A6061P-T651

JIS規格アルミニウム及びアルミニウム合金板

JIS-H 4000

| 板厚 (mm) | 1000×2000 (mm) | 1250×2500 (mm) | 1525×3050 (mm) | 2000×4000 (mm) | 引張強さ N/mm ² | 耐力 N/mm ² | 伸び % |
|---------|----------------|----------------|----------------|----------------|------------------------|----------------------|-------|
| 8.0 | ◎ | ◎ | | | 295以上 | 245以上 | 10以上 |
| 10.0 | | ◎ | ◎ | | | | |
| 12.0 | | ◎ | ◎ | | | | |
| 15.0 | | ◎ | ◎ | | | | 9以上 |
| 20.0 | | ◎ | ◎ | | | | |
| 25.0 | | ◎ | ◎ | ◎ | | | |
| 30.0 | | ◎ | ◎ | | | | 8以上 |
| 35.0 | | ◎ | ◎ | | | | |
| 38.0 | | | | ◎ | | | |
| 40.0 | | ◎ | ◎ | | | | |
| 45.0 | | ◎ | ◎ | | | | |
| 50.0 | | ◎ | ◎ | | | | |
| 55.0 | | ◎ | ◎ | | | | 6以上 |
| 60.0 | | ◎ | ◎ | | | | |
| 65.0 | | ◎ | ◎ | | | | |
| 70.0 | | ◎ | ◎ | | | | |
| 80.0 | | ◎ | ◎ | | | | |
| 85.0 | | | ◎ | | | | |
| 90.0 | | ◎ | ◎ | | (295以上) | (245以上) | (6以上) |
| 100.0 | | ◎ | ◎ | | | | |
| 110.0 | | ◎ | ◎ | | | | |
| 120.0 | | ◎ | ◎ | | | | |
| 130.0 | | ◎ | ◎ | | | | |
| 140.0 | | | ◎ | | | | |
| 150.0 | | ◎ | ◎ | | | | |
| 160.0 | | ◎ | | | | | |
| 180.0 | | | ◎ | | | | |

()の数字は機械的性質の規格値がないため、メーカー標準値