



商品名

A2017P-T351

JIS規格アルミニウム及びアルミニウム合金板

JIS-H 4000

板厚 (mm)	1000×2000 (mm)	1250×2500 (mm)	1525×3050 (mm)	引張強さ N/mm ²	耐力 N/mm ²	伸び %
6.0		◎		375以上	215以上	12以上
8.0		◎				
10.0		◎				
12.0		◎				
15.0		◎				
20.0		◎				
25.0		◎				
30.0		◎				
35.0		◎	◎			
40.0		◎				
45.0		◎				
50.0		◎		355以上	195以上	11以上
55.0		◎				
60.0		◎				
70.0		◎				
80.0		◎				
90.0		◎				(355以上)
100.0		◎				
120.0		◎	◎			
150.0			◎	(355以上)	(195以上)	(10以上)

()の数字は機械的性質の規格値がないため、メーカー標準値